

KORATECT® SL 12

Brief description **KORATECT® SL 12** is a special mixture of isomeric octyltriethoxysilanes with iso-octyltriethoxysilane as main component.

Product properties **KORATECT® SL 12** is suitable for mass hydrophobization of large concrete volumes. The use of **KORATECT® SL 12** leads to a significant reduction of efflorescence in combination with a significant reduction of water and chloride adsorption. Furthermore the freeze-thaw resistance is improved. Under favourable conditions even the growth of moss or algae on the concrete surface is lowered significantly. The pores of the building material are not blocked by **KORATECT® SL 12** and the appearance of the surface is usually not affected.

Application **KORATECT® SL 12** can be directly added to the dry concrete mixture e. g. by spraying. In this way a complete permeation of the concrete with the impregnating agent can be achieved, leading to an even better long term durability. Furthermore a costly and time consuming after-treatment can be avoided.

The dosage should be in range of 0.2 % w/w and can be used as start-up value but the dosage should be determined by individual tests. The dosage is given with reference to the weight of cement of the concrete mixture.

	Aircontent in V-%	Water absorption in %		Compressive Strength _{cube} in %
		7 days	28 days	
untreated	1.15	100	100	100
KORATECT® SL 12 0,2 % ¹⁾	1.0	31	46	87

¹⁾ Addition by weight of cement

Product information*

Appearance	: Clear, colorless
Active substance content in % w/w	: Approx. 99
Density at 20 °C in g/mL	: Approx. 0.90
Viscosity at 25 °C in mm ² /s	: Approx. 1.9

Shelf life Sealed in its original container and at storage temperatures between +5 °C and +40 °C, **KORATECT® SL 12** has a shelf life of 12 months. The containers must be protected from direct sunlight and the product stirred well before decanting.

If the product is stored for longer than the date or period specified on the label, it does not necessarily mean that the product is unfit for use. In this case a review of the property values required for the intended use is essential for reasons of quality assurance.

KORATECT® SL 12

For more information on product safety and handling, please refer to the safety data sheet.

Our technical advice whether spoken, written or through test trials is given to the best of our knowledge, is to be understood as non-binding in character and in relation to any possible industrial property rights of third parties; it is not a substitute for your, the buyer's, own tests and trials on the products supplied by us to determine whether they are suitable for the intended processes and purposes. The application, use and processing of the products are beyond our control and, therefore, entirely your own responsibility. In the event that a liability is nevertheless considered, any compensation will be limited to the value of the goods supplied by us and used by you. Of course, we guarantee the perfect quality of our products according to our general terms and conditions.

*This information is intended as a guide and should not be used in preparing specifications

**Kurt Obermeier GmbH & Co. KG, Berghäuser Str. 70 - D-57319 Bad Berleburg, Germany Tel.: +49 (0) 2751 524-0
Fax: +49 (0) 2751 5041, email: info@obermeier.de www.obermeier.de**